

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau




(43) International Publication Date  
4 March 2004 (04.03.2004)

PCT

(10) International Publication Number  
**WO 2004/019177 A2**

- (51) International Patent Classification<sup>7</sup>: **G06F** (74) Agent: MILLER, Courtney, J.; 1100 Fifth Third Center, 21 East State Street, Columbus, OH 43215 (US).
- (21) International Application Number: PCT/US2003/026459 (81) Designated States (*national*): CA, JP, KP, KR, US.
- (22) International Filing Date: 22 August 2003 (22.08.2003) (84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- (25) Filing Language: English Declaration under Rule 4.17:  
— of inventorship (Rule 4.17(iv)) for US only
- (26) Publication Language: English Published:  
— without international search report and to be republished upon receipt of that report
- (30) Priority Data: 60/405,532 23 August 2002 (23.08.2002) US
- (71) Applicant and (72) Inventor: KIM, Sang-Soo [KR/US]; 7245 Edgewood Lane, Athens, OH 45701 (US). For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: DEVICE AND METHOD FOR TESTING PAVING MATERIALS



(57) Abstract: A device and method for directly measuring the critical temperatures for thermal cracking of asphalt binders. The exemplary comprises a metal ring, a strain gauge attached to the inner surface of the ring, an environmental chamber, one or more signal amplifiers, and a data acquisition system such as a laptop computer running suitable data analysis software. A thermocouple may also be attached to the inside of the tube to closely monitor the ring temperature. A mold that is also a component of the present invention is used to create a circular asphalt binder test specimen. When properly cast the specimen encircles the metal ring. The specimen and ring are placed within the environmental chamber for analysis. Development of thermal stress (induced by temperature reduction within the environmental chamber) within the asphalt binder test specimen is monitored by the strain gauge and the cracking temperature is directly determinable from the strain reading.